

MAESTRO

ВОЗДУХОПРОНИЦАЕМАЯ СУПЕРУКРЫВИСТАЯ КРАСКА НА ВОДНОЙ ОСНОВЕ ДЛЯ ВНУТРЕННИХ РАБОТ

code 4820019

ОПИСАНИЕ

MAESTRO - воздухопроницаемая краска на водной основе с высокой укрывистостью, предназначенная для окраски внутренних поверхностей стен. Виниловые смолы, входящие в состав, устойчивы к щелочным составляющим и к истиранию. MAESTRO - краска, специально разработанная для профессионального использования, так как обладает высокой укрывистостью, легкая в нанесении, хорошо растягивается, выравнивает поверхность и придает матовый аспект, в том числе в присутствии поверхностей с разной степенью впитывания.

ОСНОВА НАНЕСЕНИЯ

May be applied on:

- New and old plasters based on hydraulic binders.
- Concrete surfaces.
- Gypsum and gypsumboard surfaces.
- Old paints and wall coatings that are organic or mineral in nature, dry, compact, absorbent and cohesive.
- Mineral conglomerates of various kinds, as long as they are absorbent.

Surfaces should be adequately prepared by following the instructions given in the paragraph 'PREPARING THE SURFACE'.

Do not apply on freshly painted surfaces.

ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

- Type of binder: water-based vinyl copolymer
- Specific gravity UNI EN ISO 2811-1: 1.70 ± 0.05 kg/l
- Viscosity UNI 8902: 35000 ± 4000 cps at 30 °C
- Gloss per UNI EN ISO 2813: 5-10, matt
- Drying times (at 25 C and 65% R.H.): touch dry in 1 hour; coatability after 4 hours.

ПОДГОТОВКА ПОВЕРХНОСТИ

Wall surfaces:

- Make sure that the surface is thoroughly dried and aged. Resurface or consolidate using specific products if necessary.
- If mold is present, treat the surface with COMBAT 222 cleanser code 4810222, and with COMBAT 333 reconstruction code. 4810333. If necessary, add the sanitizing agent COMBAT 444 code 4810444 to the product.
- Brush or wash to remove any efflorescence and any old peeling paint. Completely eliminate any raised layers of lime-based or tempera paints.
- Remove any dust, smog or other deposits by brushing.
- Level any irregularities in the surface and treat holes, cracks, crevices and gaps with TAMSTUCCO 9400006/9410110. Use adequate sealants to seal any cracks.
- sand putty and touch-ups with sandpaper; remove dust.
- Smooth if necessary with RASAMIX 9440160 or with BETOMARC 9450150 or RASOMARC 9500150 according to the type of support.
- Bond with a coat of IDROFIS 4700006 acrylic

water-based wall fixative or ATOMO 8840001 micronized solvent-free fixative. On plasterboard, apply the specific fixative PREPARA 4710019 pigmented fixative. Generally, on highly chalking surfaces, in the presence of thin layers of old tempera or deteriorated paints, apply one coat of ISOMARC 4410111 solvent-based fixative or ATOMO 8840001 micronized solvent-free fixative.

- Apply MAESTRO as described in the application instructions.

*(The dilution of the fixative and amounts to be applied depend on the absorption of the support surface, and must be determined through preliminary tests on the specific support surface - See the relevant technical data sheet).

ИНСТРУКЦИИ ПО НАНЕСЕНИЮ

- Air and support surface conditions:

Air temperature: Min. +8 °C / Max. +35 °C

Relative environmental humidity: <75%

Support surface temperature: Min. +5 °C / Max. +35 °C

Moisture level of the support surface: <10%

- Tools: brush, roller, spray gun or airless.

- N coats: at least 2 coats of the product should be applied.

- Diluting: base coat at 35-40% with water; subsequent coats at 30%

- When spraying and airless spraying thinning varies depending on the unit and operating pressure used.

- Tools should be cleaned immediately after use using water.

- Indicative spreading rate: 8-10 sqm/l per coat based on smooth surfaces featuring average absorption. It is advisable to determine the actual spreading rate by carrying out a preliminary test on the specific surface.

КОЛЕРОВКА

The product may be tinted by means of the Marcromie Color Matching System. The product may also be tinted using BRAVOCASA TINTE COLORANTI series 408P (in light shades only) and COLORADO series 548 colorants.

When using multiple batches it is recommended to remix the various products together to avoid slight differences in shading.

ХРАНЕНИЕ

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 2 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

УКАЗАНИЯ ПО ТЕХНИКЕ БЕЗОПАСНОСТИ

Произведено в соответствии с директивами Евросоюза (2004/42/EC)

Категория A/a: краска матовая для стен и потолка для внутренних работ (блеск≤25@60°) (на водной основе): 30 г/л (2010) Содержит макс.: 30 г/л VOC

Применять материал согласно действующим нормам гигиены и безопасности; после использования запре-

MAESTRO

ВОЗДУХОПРОНИЦАЕМАЯ СУПЕРУКРЫВИСТАЯ КРАСКА НА ВОДНОЙ ОСНОВЕ ДЛЯ ВНУТРЕННИХ РАБОТ

code 4820019

щено выбрасывать упаковки в окружающую среду, остатки материала должны быть полностью высушены и утилизированы вместе со строительными отходами. Не выбрасывать отходы материала в канализацию, водоемы и на землю. Для дополнительной информации необходимо ознакомиться с Листом Безопасности.

КРАТКОЕ ОПИСАНИЕ

Application, on previously prepared surfaces, of MAESTRO Low-gloss vinyl emulsion paint featuring a high level of transferability for interior use cod. 4820019 - with water-based vinyl resin base - with at least 2 coats of a quantity determined by the absorption of the surface.

Supply and application of the material €. per sq m.

Il SAN MARCO GROUP garantisce, che l'informazione presentata è basata sui migliori risultati della nostra esperienza e delle nostre conoscenze tecnico-scientifiche; tuttavia non può assumersi alcuna responsabilità per i risultati ottenuti, in quanto le condizioni di applicazione non sono sotto il nostro diretto controllo. Consigliamo sempre di verificare l'idoneità del materiale in ogni caso specifico. Questo descrittivo tecnico annulla e automaticamente sostituisce tutti i precedenti. Per qualsiasi informazione tecnica rivolgersi al personale tecnico SAN MARCO GROUP al telefono: +39 041 4569322.