

MARCONOL VERNICE NITRO

SATIN AND GLOSS FINISH FOR INTERIOR USE

code 8200638/619

DESCRIPTION

MARCONOL VERNICE NITRO is a quick-drying product for painting wooden articles indoors, with a base of synthetic resins and nitrocellulose, featuring good filling power and dilatation.

INSTRUCTIONS FOR USE

The product is suitable for application on woodwork indoors which has previously been treated with MARCONOL FONDO TURAPORI code 8100031.

TECHNICAL SPECIFICATIONS

- Type of Binder: synthetic resins and nitrocellulose
- Solvent: aliphatic hydrocarbons
- Specific gravity per UNI EN ISO 2811-1: 0.95 ± 0.05 kg/l
- Viscosity per UNI 8902: 4000 ± 200 cps at 25 °C (Brookfield rotational viscosimeter)
- Gloss per UNI EN ISO 2813:
.8200619 Gloss: >85 Gloss at 60°
.8200638 Satin-finish: 20 ± 5 at 60°
- Drying time (at 25 °C and 65% R.H.): to touch in 15'; to recoat after 2 hours.

PREPARING THE SURFACE

Woodwork:

- Sand lightly in order to remove the raised wood fibres.
- Remove any resin using a suitable thinner.
- Fill the imperfections with synthetic filler. Rub down the fillings and eliminate any dust.
- Make sure the wood is not too damp.
- Apply 1-2 coats of MARCONOL FONDO TURAPORI 8100031.
- After at least 2 hours, proceed with the application of MARCONOL VERNICE NITRO according to the procedures described under "Indications for product application".

APPLICATION INSTRUCTIONS

Air and surface conditions:

Air temperature: Min. +5 C / Max. +35 C.

Relative humidity of the air: <80%.

Temperature of the surface: Min. +5 C / Max. +35 C.

Humidity of the surface: <10% R.H.

- N coats: at least 2 coats of the product should be applied.
- Tools: spray gun.
- Thinning: 60-70% with Anti-blush nitro thinner 5170076.
- Tools should be cleaned immediately after use using Anti-blush nitro thinner 5170076.
- Indicative spreading rate: 5-6 sq m/l based on 2 coats on surfaces featuring average absorption. It is advisable to perform a preliminary test on the specific surface in order to determine the actual consumption.

TINTING

STORAGE

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 3 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

SAFETY RULES

Dir. 2004/42/EC not applicable

Harmful - Highly flammable

Contains Xilene

The product must be transported, used and stored in accordance with the standards in force regarding hygiene and safety; after use, do not litter, let residues dry out completely and treat them as special waste. Consult the safety data sheet for additional information.

SPECIFICATION ITEM

Application, on preprepared surfaces, of MARCONOL VERNICE NITRO Gloss and satin-finish varnish for interior use - with a base of synthetic resins and nitrocellulose - with at least 2 coats of a quantity determined by the absorption of the surface
Supply and application of the material €. per sq m.

SAN MARCO GROUP guarantees that the information herein is provided to the best of its technical and scientific knowledge and based on its experience; nonetheless, the company may not be held liable for the results obtained using these products, as application conditions are beyond its control. It is recommended to always make sure that the product is suited to each specific instance. The present sheet voids and replaces any previously existing sheets. For further technical information call the technical service +39 041 4569322.