

UNIMARC FINITURA LEGNO

ЗАЩИТНАЯ ПРОЗРАЧНАЯ ВОДОРАСТВОРИМАЯ КРАСКА БЕЗ ЗАПАХА ДЛЯ ВНУТРЕННИХ И НАРУЖНЫХ РАБОТ

code 3180638/819

ОПИСАНИЕ

UNIMARC FINITURA LEGNO - водорастворимая краска для защиты и декорирования деревянных поверхностей для внутренних и внешних работ. Связующее вещество на основе акриловых сополимеров и специальных добавок, поглощающих ультрафиолетовые лучи, позволяет применять материал также для внешних работ в условиях сильного воздействия атмосферных осадков и солнечных лучей. Пленка материала остается очень эластичной и постоянной, несмотря на естественные структурные изменения древесины.

ОСНОВА НАНЕСЕНИЯ

The product is suitable for exterior and interior use and can be applied on wood:

New, old or varnished woodwork such as matchboarding, lofts, windows, balconies, fences, shutters, stairs, etc..

- Pay attention to the treatment of woods rich in tannin. To prevent the formation of unaesthetic dark stains apply UNIMARC PRIMER ANTITANNINO cod. 3080001/0019.

ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

-Type of binder: water-based acrylic resin

-Solvent: water

-Specific gravity per UNI EN ISO 2811-1: 1.00-1.10 kg/l

-Viscosity UNI 8902: 800±75 cps at 25 °C (Brookfield rotational viscometer)

-Gloss per UNI EN ISO 2813:

.3180819 glossy: >85, at 60°

.3180638 silk: 20±5, at 60°

- Drying times (at 25 C and 65% R.H.): touch dry in 1 hour; coatability after 6 hours.

ПОДГОТОВКА ПОВЕРХНОСТИ

New woodwork:

- Sand lightly in order to remove the raised wood fibres.

- Remove any resin using the Nitro thinner 5170076.

- Fill the imperfections with synthetic filler. Rub down the fillings and eliminate any dust.

- Make sure the wood is not too damp.

- On woodwork featuring irregular absorption, or on soft or dry wood, apply an undercoat of clear UNIMARC IMPREGNANTE LEGNO series 313, thinned at 20-30% with water.

- For exterior applications, in order to increase the degree of protection of the surface, it is advisable to apply two coats of coloured UNIMARC IMPREGNANTE LEGNO series 313.

- For interior applications, 2 coats of UNIMARC FINITURA LEGNO can be applied directly, sanding between coats.

- Sand the surfaces and then proceed with the application of 2 coats of UNIMARC FINITURA LEGNO, sanding between coats in order to remove the raised fibres.

Varnished woodwork:

- Sand down in order to remove the raised wood fibres.

- Eliminate any coats of old flaking varnish and coarsen all the surfaces which have already been varnished.

- Remove any resin using the Nitro thinner 5170076.

- Fill the imperfections with synthetic filler. Rub down the fillings and eliminate any dust.

- Make sure the wood is not too damp.

- On woodwork featuring irregular absorption, or on soft or dry wood, apply an undercoat of clear UNIMARC IMPREGNANTE LEGNO series 313, thinned at 20-30% with water.

- For exterior applications, in order to increase the degree of protection of the surface, it is advisable to apply two coats of coloured UNIMARC IMPREGNANTE LEGNO series 313.

- For interior applications, 2 coats of UNIMARC FINITURA LEGNO can be applied directly, sanding between coats.

- Sand the surfaces and then proceed with the application of 2 coats of UNIMARC FINITURA LEGNO, sanding between coats in order to remove the raised fibres.

ИНСТРУКЦИИ ПО НАНЕСЕНИЮ

- Air and surface conditions:

Air temperature: Min. +8 °C / Max. +35 °C.

Relative humidity of the air: <75%.

Temperature of the surface: Min. +5 °C / Max. +35 °C.

Humidity of the surface: <10% R.H..

- Avoid applying the product when there is condensation on the surface, or in direct sunlight.

- Tools: brush or spraygun.

- Stir the product carefully before use.

- Diluting: by brush ready to be used; by spraying at 5% max with water.

- Apply the product as it is in successive coats, allowing at least 6 hours between coats.

- The product is ready to be used.

- N coats: 2 coats of product are required for interior use and wherever environmental conditions are not particularly harsh; if this is not the case, and on new wood, at least 3 coats are recommended.

- Tools should be cleaned using water immediately after use.

- Indicative spreading rate: 5-6 sq m/l based on 2 coats on wood featuring average absorption.

КОЛЕРОВКА

The product is compatible with the colouring pastes of the Marcromie tinting system (up to max. 5%).

ХРАНЕНИЕ

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 3 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

УКАЗАНИЯ ПО ТЕХНИКЕ БЕЗОПАСНОСТИ

EU limit value (Dir. 2004/42/EC)

Cat. E: Interior/exterior trim varnishes and woodstains (water base): 150 g/l (2007) / 130 g/l (2010)

UNIMARC FINITURA LEGNO Contains max: 30 g/l VOC

UNIMARC FINITURA LEGNO

ЗАЩИТНАЯ ПРОЗРАЧНАЯ ВОДОРАСТВОРИМАЯ КРАСКА БЕЗ ЗАПАХА ДЛЯ ВНУТРЕННИХ И НАРУЖНЫХ РАБОТ

code 3180638/819

The product does not require labelling in accordance with 67/548/EEC and 1999/45/EC and its subsequent changes and updates. Use the product according to current health and safety regulations; after use, do not discard the containers in the environment; allow the residue to dry thoroughly, then treat as special waste. Store out of the reach of children. Use in a well ventilated place. In case of contact with eyes, wash immediately with abundant running water. In case of ingestion, see a physician immediately and show him or her the container or label. Do not dispose of residues in the sewers, waterways or ground. For more information consult the safety data sheet.

КРАТКОЕ ОПИСАНИЕ

Applications, on preprepared woodwork, of UNIMARC FINITURA LEGNO Clear preservative varnish for exterior-interior use cod. 3180819/3180638 - with a water-based acrylic resin base - with at least 2 coats of a quantity determined by the absorption of the surface
Supply and application of the material €. per sq m.

Il SAN MARCO GROUP garantisce, che l'informazione presentata è basata sui migliori risultati del nostro know-how e delle nostre conoscenze tecnico-scientifiche, ma non può assumersi alcuna responsabilità per i risultati ottenuti, in quanto le condizioni di applicazione non sono sotto il nostro diretto controllo. Consigliamo sempre di verificare l'adeguatezza del prodotto in ogni caso specifico. Il presente tecnico descrittivo annulla e automaticamente sostituisce tutti i precedenti. Per qualsiasi informazione tecnica rivolgersi al personale tecnico SAN MARCO GROUP al numero telefonico: +39 041 4569322.