

**SAN MARCO**  
is a brand of  
San Marco Group Spa

[www.san-marco.com](http://www.san-marco.com)

SAN MARCO GROUP  
Via Alta 10/A - 30020  
Marcon (Venezia), Italia

info@sanmarcogroup.com  
+39 041 4569322  
[www.sanmarcogroup.com](http://www.sanmarcogroup.com)

# Allover Base

DECORATIVE PRIMER/FINISH COATING FOR CONTINUOUS FLOORS AND WALLS -  
FOR THE SINGLE-COMPONENT ALLOVER SYSTEM



SERIES 892

ALLOVER BASE - V.2024-09-24

## DESCRIPTION

ALLOVER BASE is a spreadable paste product specifically designed to create both an anchoring primer and textured, textured finishes on horizontal and vertical interior surfaces. It provides high direct adhesion on substrates such as concrete, old resin floors, and tiles. This product can be coloured using the tinting system.

## INSTRUCTIONS FOR USE

Due to its characteristics, it meets a wide range of aesthetic performance requirements in living rooms, bathrooms, kitchens, restaurants, studios/offices, shops, showrooms, wellness/spa areas, and can also be used to decorate furnishings. The ALLOVER System is easily implemented on-site and can be applied directly on concrete floors, old ceramic floors, walls.

## TECHNICAL SPECIFICATIONS

- Binder nature: silanized acrylic copolymer in water emulsion
- Solvent: water
- Appearance: white thixotropic paste
- Max. aggregate size: <0.75 mm
- Density UNI EN ISO 2811-1:  $1.58 \pm 0.05$  kg/l
- Abrasion resistance TABER - grinding wheel H22 500 g 200 rpm at 7 days <0.9 g
- Workability time: approx. 40 minutes at 20°C, RH=60%.
- Overcoating time: after 4 hours at 20°C, RH=60%.
- Drying (at 25 °C and 65% R.H.): to the touch in 1 hour; overcoatable after 4 hours (variable depending on ambient and substrate conditions). For ALLOVER systems:
- Indoor Air Quality Classification: A+
- Indoor Air Comfort certification: IAC-442-01-06
- Fire reaction EN 13501-1: Class B fl s1

Refers to consumption not exceeding that indicated, and application on a non-combustible surface.

## PREPARING THE SURFACE

Refer to the ALLOVER installation manual

## APPLICATION INSTRUCTIONS

Environment and background conditions:

Ambient temperature: Min. +10 °C / Max. +35 °C

Relative humidity of the environment: <75%

Background temperature: Min. +10 °C / Max. +35 °C

Background humidity: <4%

- Tools: stainless steel spatula/trowel

- Layers: 1 to 3 depending on the effect desired

- Dilution: ready to use

- Cleaning of tools should be done with water immediately after use

- Yield: 0.6-0.8 kg/m<sup>2</sup> per layer depending on background - 1 kg/m<sup>2</sup> if glass-fibre mesh is used. For more information on installing the systems ("SMART," "FLAT," "FLAT Fast") please refer to the ALLOVER installation manual.

Further information on the performance of the ALLOVER systems, please contact the San Marco technical support team.

## TINTING

The product may be tinted by means of the Color Matching System.

When using multiple batches it is recommended to remix the various products together to avoid slight differences in shading.

## STORAGE

Maximum temperature for storage stability: +35 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 2 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

## SAFETY RULES

EU limit value (Dir. 2004/42/EC)

Cat. A/I: decorative effect coatings (water-base): 200 g/l (2010)

The product contains max: 5 g/l VOC

Use the product according to current health and safety regulations; after use, do not discard the containers in the environment; allow the residue to dry thoroughly, then treat as special waste. Do not dispose of residues in the sewers, waterways or ground. For more information consult the safety data sheet.