

SAN MARCO

is a brand of
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia

info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Dolomite

WASHABLE WATER-BASED COVERING MATT WHITE PAINT - FOR PROFESSIONAL USE



SERIES 355

DOLOMITE - V.2024-09-23

DESCRIPTION

DOLOMITE is a water-based paint formulated for professional users. Its ease of application, low-drip, and uniform white finish make it ideal for the shipbuilding industry.
It is odourless, low-VOC, and formaldehyde-free.

TECHNICAL SPECIFICATIONS

- Type of Binder: Acrylic copolymer in aqueous dispersion
- Indoor Air Quality classification: A+

Classification per UNI EN 13300:

.Wet-scrub resistance per ISO 11998: class 3

.Gloss per EN ISO 2813: <5, dead matt

.Hiding power per ISO 6504-3: class 1 on 7 mq/l spreading rate

Other characteristics

- Specific gravity per UNI EN ISO 2811-1: 1.65±0.05 kg/l

- Wet-scrub resistance per UNI 10560: >1000 cycles, resistant

- Classification of reaction to fire EN13501-1: Class A2 s1 d0

Referred to a consumption not exceeding that indicated, and to an application on a non-combustible surface.

- Drying time (at 25 °C and 65% R.H.): to touch in 1 hour; to recoat after 3 hours.

INSTRUCTIONS FOR USE

May be applied on:

- New and old plasters based on hydraulic binders.
- Concrete surfaces.
- Gypsum and gypsumboard surfaces.
- Old paints and wall coatings that are organic or mineral in nature, dry, compact, absorbent and cohesive.
- Mineral conglomerates of various kinds, as long as they are absorbent.

Surfaces should be adequately prepared by following the instructions given in the paragraph 'PREPARING THE SURFACE'.
Do not apply on freshly-painted and alkaline-tending surfaces, and allow adequate curing time, typically four weeks.

PREPARING THE SURFACE

Plaster, gypsum and gypsumboard surfaces:

- Make sure that the surface is thoroughly dried and aged. Resurface or consolidate using specific products if necessary.
- If mold is present, treat the surface with COMBAT 222 cleanser code 4810222, and with COMBAT 333 reconstruction code 4810333. if necessary, add COMBAT 444 code 4810444 sanitizer to the product.
- Brush or wash to remove any efflorescence and any old peeling paint. Completely eliminate any raised layers of lime-based or tempera paints.
- Remove any dust, smog or other deposits by brushing.
- Level any irregularities in the surface and treat holes, cracks, crevices and gaps with TAMSTUCCO 9400006/9410110; sand putty and touch-ups with sandpaper.
- Use adequate sealants to seal any cracks.
- Smooth if necessary with RASAMIX FIT 9670160 or with BETOMARC FIT 9740150 or MARCOPRO according to the type of support.
- On a clean, dry surface apply one coat of IDROFIS 4700006 acrylic water-based wall fixative or ATOMO 8840001 micronized solvent-free fixative. On gypsumboard, apply the specific fixative PREPARA 4710019 pigmented fixative. In the presence of thin layers of old tempera or chalking paints, apply one coat of solvent-based wall fixative ISOMARC 4410111 or ATOMO 8840001 micronized solvent-free fixative.
- Proceed with applying the finishing product.

*(The dilution of the fixative and amounts to be applied depend on the absorption of the support surface, and must be determined through preliminary tests on the specific support surface - See the relevant technical data sheet).

APPLICATION INSTRUCTIONS

- Air and support surface conditions:
Air temperature: Min. +8 °C / Max. +35 °C
Relative environmental humidity: <75%
Support surface temperature: Min. +5 °C / Max. +35 °C
Moisture level of the support surface: <10%
- Tools: brush, roller, airless.
- N coats: at least 2 coats of the product should be applied.
- Dilution: with water
.roller: 20-25%
.brush: 40-45%
.airless: 20-25% (nozzle diameter: 0.45-0.53 mm / 0.018-0.021 in.; pressure: 150-180 bar / 2176-2611 psi)
- Tools should be cleaned immediately after use using water.
- Indicative spreading rate: 10-11 sqm/l per coat based on smooth surfaces featuring average absorption. It is advisable to determine the actual spreading rate by carrying out a preliminary test on the specific surface.

TINTING

The product is white. The product may be tinted using COLORADO series 548 colorants up to 5%.
When using multiple batches it is recommended to remix the various products together to avoid slight differences in shading.

STORAGE

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 2 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

SAFETY RULES

Limit value EU (Dir. 2004/42/EC)

Cat. A/a: Matt coatings for interior walls and ceilings (gloss≤25@60°) (water-base): 30 g/l (2010)

The product contains max: 1 g/l VOC

Use the product according to current standards of hygiene and safety after use, do not litter containers, allow the residue to dry and treat them as special waste. Do not empty into drains, water courses or onto the ground. For more information see the safety data sheet.

SPECIFICATION ITEM

Professional washable water-based paint for interiors

Application, on pre-prepared surfaces, of DOLOMITE series 355 washable water-based paint based on acrylic polymers in water dispersion, in at least 2 layers in the amounts determined by substrate absorption.

Supply and application € per sq.m.