

SAN MARCO
is a brand of
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia

info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Combat 777

ВОЗДУХОПРОНИЦАЕМАЯ ЭКОЛОГИЧЕСКИ ЧИСТАЯ КРАСКА НА ВОДНОЙ
ОСНОВЕ С ЗАЩИТОЙ ОТ ПЛЕСЕНИ ДЛЯ ВНУТРЕННИХ РАБОТ



CODE 4870777

COMBAT 777 - V.2024-09-24

ОПИСАНИЕ

СОМБАТ 777 - вододисперсионная, воздухопроницаемая краска, разработана для декорации и защиты внутренних работ от образования конденсата и влажности, и развития плесени. Материал на долгое время предохраняет внешний вид поверхности и обладает гигиеническим эффектом, улучшая Жилищный Комфорт. СОМБАТ 777 - обладает хорошей укрываемостью, высокой воздухопроницаемостью и легок в нанесении.

ОСНОВА НАНЕСЕНИЯ

May be applied on:

- New and old plasters based on hydraulic binders.
- Concrete surfaces.
- Gypsum and gypsumboard surfaces.
- Old paints and wall coatings that are organic or mineral in nature, dry, compact, absorbent and cohesive.
- Mineral conglomerates of various kinds, as long as they are absorbent.

Surfaces should be adequately prepared by following the instructions given in the paragraph 'PREPARING THE SURFACE'.

Do not apply on freshly painted surfaces.

ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

- Nature of the binder: vinylversatate copolymer in emulsion.
- Specific gravity per UNI EN ISO 2811-1: 1.70 ± 0.05 kg/l
- Gloss per EN ISO 2813: 5-10, matt
- Classification of reaction to fire EN13501-1: Class A2 s1 d0

Referred to a consumption not exceeding that indicated, and to an application on a non-combustible surface.

- * Anti-mold efficacy per UNI 9805: 0 = no development
- * Resistance to fungi per UNI EN 15457: 0 = no development
- Drying time (at 25 °C and 65% R.H.): to touch 30 minutes; to recoat after 4

hours.

ПОДГОТОВКА ПОВЕРХНОСТИ

Wall and ceiling surfaces:

- Make sure that the surface is thoroughly dried and aged. Resurface or consolidate using specific products if necessary.
- If mold is present, treat the surface with COMBAT 222 cleanser code 4810222, and with COMBAT 333 reconstruction code 4810333. To protect the wall from mold formation add COMBAT 444 code 4810444 sanitizer to the product.
- Brush or wash to remove any efflorescence and any old peeling paint. Completely eliminate any raised layers of lime-based or tempera paints.
- Remove any dust, smog or other deposits by brushing.
- Level any irregularities in the surface and treat holes, cracks, crevices and gaps with TAMSTUCCO 9400006/9410110; sand putty and touch-ups with sandpaper.
- Use adequate sealants to seal any cracks.
- Smooth if necessary with RASAMIX 9440160 or with BETOMARC 9450150 or RASOMARC 9500150 according to the type of support.
- On a clean, dry surface apply one coat of IDROFIS 4700006 acrylic water-based wall fixative or ATOMO 8840001 micronized solvent-free fixative. On gypsumboard, apply the specific fixative PREPARA 4710019 pigmented fixative. In the presence of thin layers of old tempera or chalking paints, apply one coat of solvent-based wall fixative ISOMARC 4410111 or ATOMO 8840001 micronized solvent-free fixative.
- Apply COMBAT 777.

*(The dilution of the fixative and amounts to be applied depend on the absorption of the support surface, and must be determined through preliminary tests on the specific support surface - See the relevant technical data sheet).

ИНСТРУКЦИИ ПО НАНЕСЕНИЮ

- Air and support surface conditions:

Air temperature: Min. +8 °C / Max. +35 °C

Relative environmental humidity: <75%

Support surface temperature: Min. +5 °C / Max. +35 °C

Moisture level of the support surface: <10%

- Tools: brush, roller, spray gun or airless.

- N. of coats: 2 coats.

- Diluting: with water. First coat at 40%; second coat at 20-30%.

- When airless spraying thinning varies depending on the unit and operating pressure used.

- Tools should be cleaned immediately after use using water.

- Indicative spreading rate: 7-8 sqm/l per coat based on smooth surfaces featuring average absorption. It is advisable to determine the actual spreading rate by carrying out a preliminary test on the specific surface.

КОЛЕРОВКА

Колеровка осуществляется по системе Tintometrico.

Материал может быть окрашен красителями COLORADO серия 548. В случае использования различных партий колерованного материала, советуем вновь перемешать между собой упаковки во избежание различия в тональности.

ХРАНЕНИЕ

Максимальная температура хранения материала: +30°C

Минимальная температура хранения: +5°C

Срок хранения материала составляет 2 года при условии хранения в закрытых оригинальных упаковках при соблюдении надлежащих правил хранения и температурного режима.

УКАЗАНИЯ ПО ТЕХНИКЕ БЕЗОПАСНОСТИ

Произведено в соответствии с директивами Евросоюза (2004/42/EC)

Категория A/α: краска матовая для стен и потолка для внутренних работ (блеск ≤ 25@60°) (на водной основе): 30 г/л (2010) Содержит макс.: 30 г/л VOC

Применять материал согласно действующим нормам гигиены и безопасности; после использования запрещено выбрасывать упаковки в окружающую среду, остатки материала должны быть полностью высушены и утилизированы вместе со строительными отходами. Не выбрасывать отходы материала в канализацию, водоемы и на землю. Для дополнительной информации необходимо ознакомиться с Листом Безопасности.

КРАТКОЕ ОПИСАНИЕ

Applications, on previously prepared surfaces, of mould-resistant emulsion paint COMBAT 777 cod. 4870777, with a base of vinylversatic resins dispersed in water and additives preserving the surface against mould growth, with the application of at least 2 coats of a quantity determined by the level of absorption of the surface.

Supply and application of the material €. per m2.