

SAN MARCO
is a brand of
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia

info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Marconol Flatting

ГЛЯНЦЕВАЯ КРАСКА НА ОСНОВЕ СИНТЕТИЧЕСКИХ МАСЕЛ ДЛЯ ДЕРЕВА



CODE 8460619

MARCONOL FLATTING - V.2024-09-24

ОПИСАНИЕ

MARCONOL FLATTING - материал на основе синтетических смол для окрашивания деревянных конструкций для внутренних и внешних работ, обладает хорошей эластичностью, что позволяет растягиваться пленке и принимать размер основы. Пленка MARCONOL FLATTING обеспечивает хорошую декоративную способность и декоративные свойства.

ОСНОВА НАНЕСЕНИЯ

The product can be applied on wood both outdoors and in:
Old, new or varnished woodwork such as matchboarding, lofts, balconies, fences, shutters, stairs, etc.

ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

- Type of Binder: synthetic resin with a high oil length
- Solvent: mix of aliphatic hydrocarbons
- Specific gravity per UNI EN ISO 2811-1: 0.92 ± 0.05 kg/l
- Viscosity per UNI 8902: 400 ± 50 cps at 25 °C (Rotathinner rotational viscosimeter)
- Gloss per UNI EN ISO 2813: >90 at 60°
- Drying (at 25 C and 65% R.H.):
 - . dust free in 2 hours;
 - . touch dry in 6 hours;
 - . coatability after 12 hours.

ПОДГОТОВКА ПОВЕРХНОСТИ

- New woodwork:
- Sand lightly in order to remove the raised wood fibres.
 - Remove any resin using a suitable thinner.
 - Fill the imperfections with synthetic filler. Rub down the fillings and eliminate any dust.
 - Make sure the wood is not too damp.

- On soft and dry wood, or excessively absorbent wood, apply a coat of coloured MARCONOL IMPREGNANTE series 843 or, for indoor applications, apply MARCONOL FONDO TURAPORI 8100031.

- Sand the surfaces and proceed with the application of 2 coats of MARCONOL FLATTING according to the procedures described under "Instructions for product application".

Varnished woodwork:

- Sand down in order to remove the raised wood fibres.

- Eliminate any coats of old flaking varnish and coarsen all the surfaces which have already been varnished.

- Remove any resin using a suitable thinner.

- Fill the imperfections with synthetic filler with a similar. Rub down the fillings and eliminate any dust.

- On deteriorated areas, or on excessively absorbent wood, apply a coat of coloured MARCONOL IMPREGNANTE series 843 or, for applications indoors, apply MARCONOL FONDO TURAPORI 8100031.

- Sand the surfaces and proceed with the application of 2 coats MARCONOL FLATTING according to the procedures described under "Instructions for product application".

ИНСТРУКЦИИ ПО НАНЕСЕНИЮ

Air and surface conditions:

Air temperature: Min. +5 C / Max. +35 C.

Relative humidity of the air: <80%.

Temperature of the surface: Min. +5 C / Max. +35 C.

Humidity of the surface: <10% R.H..

- Avoid applying the product when there is condensation on the surface, or in direct sunlight.

- Tools: brush, roller.

- Stir the product carefully before use.

- Thinning: ready to use.

- Application by spraying gun may be applied only in authorized factory (Dir. 2001/42/EC), thinning at 10% with White spirit 5200010.

- Apply the product as it is, allowing at least 12 hours between coats.

- N. coats: when applying indoors, and where environmental conditions are not particularly harsh, 2 coats of the product should be applied; otherwise - and in the case of new wood - it is advisable to apply 3 coats.

- Tools should be cleaned using White spirit 5200010 immediately after use.

- Indicative spreading rate: 8-9 sq m/l based on 2 coats on wood featuring average absorption. It is advisable to perform a preliminary test on the specific surface in order to determine the actual consumption.

КОЛЕРОВКА

The product is supplied in the colourless gloss version.

ХРАНЕНИЕ

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 3 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

УКАЗАНИЯ ПО ТЕХНИКЕ БЕЗОПАСНОСТИ

Limit value EU (Dir. 2004/42/EC)

Cat. A/e: interior/exterior trim varnishes and woodstains (solvent-base): 500

g/l (2007) / 400 g/l (2010)

MARCONOL FLATTING contains max: 400 g/l VOC

Flammable

The product must be transported, used and stored in accordance with the standards in force regarding hygiene and safety; after use, do not litter, let residues dry out completely and treat them as special waste. Consult the safety data sheet for additional information.

КРАТКОЕ ОПИСАНИЕ

Applications, on previously prepared surfaces, of MARCONOL FLATTING Synthetic-oil gloss wood varnish cod. 8460619 - with a base of oil-based synthetic resins dispersed in aliphatic solvents - with at least 2 coats of a quantity determined by the absorption of the surface

Supply and application of the material €. per sq m.