

SAN MARCO

is a brand of
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia

info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Neptunus Additivo Di Aggancio

MODIFIER FOR DEHUMIDIFYING MORTAR



CODE 0700250

NEPTUNUS ADDITIVO DI AGGANCIO - V.2024-09-23

DESCRIPTION

NEPTUNUS ADDITIVO DI AGGANCIO is a modifier for mortars that are cement or hydraulic lime-based. It is resistant to saponification, is strongly adhesive and able to confer upon mortars an improved adhesion to the surface and greater waterproofing.

INSTRUCTIONS FOR USE

NEPTUNUS ADDITIVO DI AGGANCIO is suggested to increase adhesion in the "fixative jet" of NEPTUNUS INTONACO DEUMIDIFICANTE, code 9480170.

TECHNICAL SPECIFICATIONS

- Type of Binder: modified acrylic resin.
- Solvent: water
- Specific gravity per UNI EN ISO 2811-1: 1.00 ± 0.02 kg/l
- Aspect: milky fluid

PREPARING THE SURFACE

Walls:

- The wall must be stripped of all mortar.
- If there is damp, remove the layer of old mortar to about 50 cms above the layer of evident damp.
- Eliminate any areas that are crumbling away and/or salt incrustations by brushing and washing with water, preferably using a pressurised-water cleaner.
- Once the surface is dry, apply a coat of NEPTUNUS ANTISALE anti-salt sealant, code 0700240, following the instructions on the relative technical sheet.
- Wait 24 hours and then apply the "mortar fixative jet" with NEPTUNUS INTONACO DEUMIDIFICANTE and the addition of NEPTUNUS ADDITIVO DI AGGANCIO.

APPLICATION INSTRUCTIONS

- Ambient and substrate conditions:
Ambient temperature: Min. $+8^{\circ}\text{C}$ / Max. $+35^{\circ}\text{C}$
Substrate temperature: Min. $+5^{\circ}\text{C}$ / Max. $+35^{\circ}\text{C}$

Method of application:

- Mix a 25 kg sack of NEPTUNUS INTONACO DEUMIDIFICANTE, code 9480170, with 5 litres of NEPTUNUS ADDITIVO DI AGGANCIO sealant additive, code 0700250 and 1 litre of water. Mix for one minute using a mechanical mixer to blend the mix well. The mixture should be very liquid and must be applied in a jet on the wall (using a trowel), without covering it altogether.
- After one hour, the "fixative jet" will be firm but not hard, and one can apply a rough coating of NEPTUNUS INTONACO DEUMIDIFICANTE.

TINTING | - - - -

STORAGE

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 2 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

SAFETY RULES

It does not fall within the scope of Legislative Decree 161/2006 (Dir. 2004/42/EC)

Causes skin irritation. May cause an allergic skin reaction. Causes serious eye damage. May irritate the respiratory tract.

Use the product in accordance with current safety and hygiene regulations; after use, do not disperse the pots in the environment; allow the residues to dry well and treat them as special waste. Do not empty into drains, watercourses or onto the ground.

For more information, please consult the safety data sheet.

SPECIFICATION ITEM | - - - -