

SAN MARCO

is a brand of
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia

info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Unimarc Finitura Cerata

COLOURED TRANSPARENT WOOD VARNISH



SERIES 312

UNIMARC FINITURA CERATA - V.2024-09-23

DESCRIPTION

UNIMARC FINITURA CERATA is a water dilutable product that protects and decorates wood, providing a satin finish. It is based on acrylic copolymer and components able to filter ultraviolet rays, transparent pigments and micro-crystalline waxes that colour the wood without masking the grain. The product is water repellent and it is particularly suited to protecting and decorating wooden structures even where they are especially exposed to atmospheric agents and the sun's rays.

The film produced by the application of the paint is particularly elastic and remains unchanged despite the natural structural variations of the wood.

INSTRUCTIONS FOR USE

May be applied to wood indoors and outdoors.

Surfaces of new and old wood, including those previously painted, such as matchboards, lofts, fixtures, balconies, fences, shutters, etc.

- Pay attention to the treatment of woods rich in tannin. To prevent the formation of unaesthetic dark stains apply UNIMARC PRIMER ANTITANNINO cod. 3080001/0019.

- Pay attention to the treatment on woods without tannin with UNIMARC FINITURA CERATA in pastel color. Apply UNIMARC PRIMER ANTITANNINO clear cod. 3080001 to prevent the natural phenomena of yellowing.

TECHNICAL SPECIFICATIONS

- Type of binder: acrylic resin in aqueous solution

- Solvent: water

- Specific gravity per UNI EN ISO 2811-1: 1.10 ± 0.05 kg/l

- Viscosity per UNI 8902: 750 ± 100 cps at 25 °C (Brookfield rotational viscometer)

- Gloss per UNI EN ISO 2813: 20-30 at 60°

- Drying times (at 25 °C and 65% relative humidity): to touch in 1 hour; to recoat after 6 hours.

PREPARING THE SURFACE

New wooden surfaces:

- Lightly sand down the surface to remove raised fibres of wood.
- Remove any resin using suitable diluent.
- Use synthetic filler to cover any imperfections. Sand down the filler and remove the dust.
- Check that the wood is not too damp.
- Apply a coat of colourless impregnating base-coat UNIMARC IMPREGNANTE LEGNO 3130300 diluted at 20-30% with water.
- On outdoor surfaces, it is recommended that two coats of coloured impregnating base-coat UNIMARC IMPREGNANTE LEGNO be applied to increase protection of the surface.
- Sand down the surfaces and apply two coats of UNIMARC FINITURA CERATA, sanding between coats to remove any raised fibres.

Previously painted wooden surfaces:

- Sand down the surface to remove raised fibres of wood.
- Remove any coats of old flaking paint and roughen all the previously painted surfaces.
- Remove any resin using suitable diluent.
- Use synthetic wood filler to cover any imperfections. Sand down the filler and remove the dust.
- Check that the wood is not too damp.
- Apply a coat of colourless impregnating base-coat UNIMARC IMPREGNANTE LEGNO over areas of degraded wood in order to render absorption more uniform.
- Sand down the surfaces and apply two coats of UNIMARC FINITURA CERATA, sanding between coats to remove any raised fibres.

In order to obtain maximum protection outdoors, it is recommended that an initial coat of coloured impregnating base-coat UNIMARC IMPREGNANTE LEGNO be applied to protect the wood, and that coloured UNIMARC FINITURA CERATA be used for greater protection, selecting the colour desired from the colour chart.

APPLICATION INSTRUCTIONS

Conditions of the surface and surroundings:

Air temperature: Min. +8 °C / Max. +35 °C.

Relative humidity of the air: <75%.

Temperature of the surface to be painted: Min. +5 °C / Max. +35 °C.

Humidity of the surface to be painted: <10%.

- Avoid applying the paint where there is surface condensation or directly under the sun.
- Tools: brush or spray gun.
- Mix the product carefully before use.
- Diluting: ready to be used.
- By spraying up to 5% with water.
- Apply the product as is in successive coats with at least 6 hours between applications.
- Number of coats: for interior use and in environmental conditions that are not especially harsh, 2 coats may be applied; in other conditions and on new wood, 3 coats are advisable.
- All tools should be washed in water immediately after use.
- Indicative coverage: 5-6 sq.m./l. applying 2 coats on wood of average absorption.

TINTING

The product is available in the colours shown on the colour chart.

Colors are obtainable via the Marcromie color matching system.

STORAGE

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 3 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

SAFETY RULES

Limit value EU (Dir. 2004/42/EC)

Cat. A/e: interior/exterior trim varnishes and woodstains (water-base): 130 g/l (2010)

The product contains max: 130 g/l VOC

Use the product according to current standards of hygiene and safety; after use do not litter containers, allow the residue to dry and treat them as special waste. For more information see the safety data sheet.

SPECIFICATION ITEM

Application, on prepared wooden surfaces, of UNIMARC FINITURA CERATA series 312 protective transparent paint, with water-based acrylic resin and sun filter, in at least 2 coats and in quantities determined by the absorption of the surface.

Supply and application of the material € per sq.m.