

SAN MARCO
is a brand of
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia

info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Unimarc Smalto Per Radiatori

ТЕРМОСТОЙКАЯ ВОДОРАСТВОРИМАЯ САТИНИРОВАННАЯ ЭМАЛЬ



CODE 3340460

UNIMARC SMALTO PER RADIATORI - V.2024-09-23

ОПИСАНИЕ

UNIMARC SMALTO PER RADIATORI -водорастворимая эмаль на основе акриловых смол для сатинированных покрытий нагревательных элементов; без запаха, подходит для нанесения на внутренние поверхности. Материал был разработан так, чтобы выдерживать высокие температуры, не вызывая разрушений, и с целью облегчения нанесения покрытия на углы и края. Акриловые смолы в водной дисперсии, входящие в состав, наделяют материал высокой моющей способностью, гарантируют устойчивость к пожелтению и хорошее сцепление с различными видами поверхности. Как и все растворимые материалы линии, UNIMARC SMALTO PER RADIATORI легко наносится и быстро высыхает.

ОСНОВА НАНЕСЕНИЯ

The product can be applied on metal heating elements:
Satin finish for radiators and convectors.
The product can be applied on radiators made from iron, cast iron and non-anodized aluminium.

ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

- Type of binder: water-based acrylic copolymer.
- Solvent: water
- Specific gravity per UNI EN ISO 2811-1: 1.23 ± 0.05 kg/l.
- Gloss per UNI EN ISO 2813: 25 ± 5 gloss at 60° (Micro Tri-Gloss).
- Viscosity per UNI 8902: 7500 ± 500 cps at 25°C (Brookfield rotational viscometer).
- Drying (25°C and 65% R.H.): to touch in 30 min.; to recoat after 6 hours.

ПОДГОТОВКА ПОВЕРХНОСТИ

- Ferrous metal:
- Employ mechanical or manual cleaning methods to remove any flakes which,

- as a result of lamination, are not perfectly adherent, along with all traces of rust.
- Remove any layers of old paint which are not perfectly adherent and sand the whole surface in order to coarsen it.
 - Remove any grease from the surface using nitro thinner.
 - Eliminate all traces of dust and dirt.
 - Apply, on a perfectly dry surface, MARCOTECH AU METAL PRIMER 3320807.
 - Apply 1-2 coats of UNIMARC SMALTO PER RADIATORI.

Galvanized surfaces, aluminium and light alloys:

- Remove all traces of oxide by means of mechanical or manual cleaning.
- Carefully remove any grease using suitable alkaline solutions or thinner.
- Remove any layers of old paint which are not perfectly adherent and sand the whole surface in order to coarsen it.
- Remove all traces of dust and, on a perfectly dry surface, proceed with the application of MARCOTECH AU METAL PRIMER 3320807 on those areas which featured the rust.
- On surfaces particularly exposed to the elements, apply 2 coats of single component PRIMER cod. 1630307 as an undercoat.
- Apply 2 coats of UNIMARC SMALTO PER RADIATORI.

ИНСТРУКЦИИ ПО НАНЕСЕНИЮ

Air and surface conditions:

Air temperature: Min. +8 °C / max. +35 °C.

Relative humidity of the air: <75%.

Temperature of the surface: Min. +5 °C / Max. +35 °C.

Dry surface.

-Tools: brush, roller, spray gun.

-Diluting: by brush and roller is ready to be used; by spraying at 10-15% with water.

-Normally two coats of the product are applied. However, the product features high hiding power and can even be applied in a single coat.

-Indicative spreading rate: 4-5 sq m/l based on 2 coats, creating a thickness of 40 microns when dry.

-Tools should be cleaned with water immediately after use.

КОЛЕРОВКА

Материал белого цвета.

ХРАНЕНИЕ

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 3 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

УКАЗАНИЯ ПО ТЕХНИКЕ БЕЗОПАСНОСТИ

Произведено в соответствии с директивами Евросоюза (2004/42/EC)

Категория A/d : краски для отделочных работ, для внутренних/наружных покрытий древесины и металлов (на водной основе): 130 г/л (2010)

Содержит не более: 130 г/л летучих органических соединений (ЛОС)

Применять материал согласно действующим нормам гигиены и

безопасности; после использования запрещено выбрасывать упаковки в окружающую среду, остатки материала должны быть полностью высушены и утилизированы вместе со строительными отходами. Не выбрасывать отходы материала в канализацию, водоемы и на землю. Для дополнительной информации необходимо ознакомиться с Листом Безопасности.

КРАТКОЕ ОПИСАНИЕ

Applications, on previously prepared surfaces, of UNIMARC SMALTO PER RADIATORI Water-based top coat paint for radiators cod. 3340460 - with acrylic resin in aqueous dispersion, for the protection of metal radiators and heating elements in general - with at least 2 coats for a minimum consumption of 200 ml/sq m.

Supply and application of the material €. per sq m.