

SAN MARCO  
is a brand of  
San Marco Group Spa

[www.san-marco.com](http://www.san-marco.com)

SAN MARCO GROUP  
Via Alta 10/A - 30020  
Marcon (Venezia), Italia

[info@sanmarcogroup.com](mailto:info@sanmarcogroup.com)  
+39 041 4569322  
[www.sanmarcogroup.com](http://www.sanmarcogroup.com)

# Unimarc Smalto Seta

ЗАЩИТНОЕ АКРИЛОВОЕ ВОДОРАСТВОРИМОЕ САТИНИРОВАННОЕ  
СРЕДСТВО БЕЗ ЗАПАХА ДЛЯ ВНУТРЕННИХ И НАРУЖНЫХ РАБОТ



SERIES 300

UNIMARC SMALTO SETA - V.2024-09-23

## ОПИСАНИЕ

UNIMARC SMALTO SETA - водорастворимое средство высокого качества на основе акриловых смол в водной дисперсии и цветных пигментов с высокой устойчивостью к свету. Акриловые смолы, входящие в состав, гарантируют отличную защиту материала от атмосферных воздействий, высокую устойчивость к пожелтению и отличную способность заполнять, растекаться и сцепляться с различными видами поверхности. UNIMARC SMALTO SETA - эмаль без запаха, невоспламеняющаяся, поэтому является подходящей для нанесения на внутренние, плохо проветренные поверхности. Как и вся продукция линии UNIMARC SMALTO SETA, данный материал предназначен для отделки высокого качества на внешних и внутренних основах из железа, цинка, легких сплавов, дерева, пластика и внутренних поверхностей стен.

## ОСНОВА НАНЕСЕНИЯ

The product can be applied on:

- new or varnished woodwork;
- suitably treated ferrous metalwork;
- galvanized surfaces, aluminium and light alloys;
- plastic (PVC);
- wall and ceiling surfaces on interior.

Pay attention to the treatment of woods rich in tannin. To prevent the formation of unaesthetic dark stains apply UNIMARC PRIMER ANTITANNINO cod. 3080001/0019.

## ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

- Type of binder: water-based acrylic copolymer
- Solvent: water
- Specific gravity per UNI EN ISO 2811-1: 1.10-1.35 kg/l depending on the colour.

- Wet-scrub resistance per ISO 11998: class 1
- Gloss per UNI EN ISO 2813: 25±5 at 60°
- Drying (25 °C and 65% R.H.): to touch in 3 hours, to recoat after 6 hours.

## ПОДГОТОВКА ПОВЕРХНОСТИ

### Ferrous metal:

- Employ mechanical or manual cleaning methods to remove any flakes which, as a result of lamination, are not perfectly adherent, along with all traces of rust.
- Remove any layers of old paint which are not perfectly adherent and sand the whole surface.
- Remove any grease from the surface using a suitable diluent.
- Eliminate all traces of dust and dirt.
- Apply MARCOTECH AU METAL PRIMER 3320807 on a perfectly dry surface.
- On surfaces particularly exposed to the elements, apply 1-2 coats of PRIMER 1630307 rust inhibiting paint as an undercoat.
- Apply 2 coats of UNIMARC SMALTO SETA.

### Galvanized surfaces, aluminium and light alloys:

- Remove all traces of oxide by means of mechanical or manual cleaning.
- Carefully remove any grease using suitable alkaline solutions or thinner.
- Remove any layers of old paint which are not perfectly adherent and sand the whole surface in order to coarsen it.
- Remove all traces of dust and, on a perfectly dry surface, proceed with the application of MARCOTECH AU METAL PRIMER 3320807 on the areas which featured the rust.
- On surfaces particularly exposed to the elements, apply 1-2 coats of single component PRIMER cod. 1630307 as an undercoat.
- Apply 2 coats of UNIMARC SMALTO SETA.

### Plastic (PVC):

- Sand the surface in order to coarsen it slightly.
- Remove any grease using a suitable diluent and clean the surface.
- Apply 2 coats of UNIMARC SMALTO SETA on a perfectly clean and dry surface.

### Woodwork:

- Sand lightly in order to remove the raised wood fibres.
- Eliminate any coats of old flaking varnish and coarsen all the surfaces which have already been varnished.
- Remove any resin using a suitable diluent.
- Fill the imperfections with synthetic filler. Rub down the fillings and eliminate any dust.
- Apply 2 coats of UNIMARC FONDO UNIVERSALE series 335 on a clean, dry surface, allowing at least 6 hours between coats or using ORIENTALITE mat primer 1450519.
- Sand the surfaces and then proceed with the application of 2 coats of UNIMARC SMALTO SETA.

### Plaster:

- Make sure the plaster has a maturing time of at least 28 days.
- Check the state of repair. The surface must be consistent. If this is not the case, take measures to reconstruct and strengthen the surface using specific products.
- Remove any efflorescence by buffing or washing.
- Where the exterior or interior surfaces feature traces of old paint, remove any parts which are flaking and which are not perfectly adherent, whilst thick coats of lime-based paint or distemper must be removed completely by wetting the

surface thoroughly and scraping, or using a water cleaning machine.

- Level any unevenness on the surface. Holes, cracks and depressions indoors can be treated using TAMSTUCCO 9400006 or TAMSTUCCO POLVERE 9410110; filling or levelling can be performed using BETOMARC 9450150 or using RASAMIX 9440160, or using other cement-based products.
- Cracks both indoors and out must be suitably widened and filled with filler or similar products.
- Rub down the fillings and repaired areas with glass-paper.
- Remove dust-, smog- and other deposits by buffing.
- Where the surface is affected by mould, treat the surfaces with COMBAT 222 Detergent 4810222 and with COMBAT 333 Restorer 4810333.
- Make sure the surface is completely dry and apply:  
Indoors, one coat of IDROFIS 4700006 acrylic water-based wall fixative or ATOMO 8840001 micronized solvent-free fixative.  
Outdoors, or indoors in the presence of thin layers of old tempera or chalking paints, one coat of solvent-based wall fixative ISOMARC 4410111 or ATOMO 8840001 micronized solvent-free fixative.
- Proceed with the application of UNIMARC SMALTO SETA.

Gypsum and gypsumboard:

- Where the surface features traces of old paint, remove any parts which are flaking and which are not perfectly adherent, remove thick coats of lime-based paint or distemper by wetting the surface thoroughly and scraping.
- Level any unevenness on the surface. Holes, cracks and depressions must be treated using TAMSTUCCO 9400006 or TAMSTUCCO POLVERE 9410110;
- Cracks must be suitably widened and filled with filler or similar products.
- Rub down the fillings and repaired areas with glass-paper.
- Remove dust-, smog- and other deposits by buffing.
- Where the surfaces are affected by mould, employ the COMBAT system (as described above).
- Make sure the surface is completely dry and apply one coat of IDROFIS 4700006 acrylic water-based wall fixative or ATOMO 8840001 micronized solvent-free fixative. On plasterboard, apply the specific fixative PREPARA 4710019 pigmented fixative.  
In the presence of thin layers of old tempera or chalking paints, one coat of solvent-based wall fixative ISOMARC 4410111 or ATOMO 8840001 micronized solvent-free fixative.
- Proceed with the application of UNIMARC SMALTO SETA.

(The thinning of the sealer and the quantity to be applied depend on the level of absorption of the surface and should be determined by performing preliminary tests on the specific surface).

## ИНСТРУКЦИИ ПО НАНЕСЕНИЮ

- Air and surface conditions:  
Air temperature: Min. +8 C / Max.+35 C.  
Relative humidity of the air: <75%.  
Temperature of the surface: Min. +5 C / Max. +35 C.  
Dry surface.
- Tools: brush, roller or spraygun.
- N. coats: at least 2 coats.
- Diluting: with water  
by brush and roller at 0-5% max  
by spraying at 10-15%.
- Tools should be cleaned with water immediately after use.
- Indicative spreading rate: 6-7 sq m/l based on 2 coats, for a thickness of 40

microns.

## КОЛЕРОВКА

Колеровка осуществляется по системе Tintometrico.  
Материал может быть окрашен красителями COLORADO серия 548.  
В случае использования различных партий колерованного материала, советуем вновь перемешать между собой упаковки во избежание различия в тональности.

## ХРАНЕНИЕ

Максимальная температура хранения материала: +30°C  
Минимальная температура хранения: +5°C  
Срок хранения материала составляет 3 года при условии хранения в закрытых оригинальных упаковках при соблюдении надлежащих правил хранения и температурного режима.

## УКАЗАНИЯ ПО ТЕХНИКЕ БЕЗОПАСНОСТИ

EU limit value (Dir. 2004/42/EC)  
Cat. B: glossy coatings for interior walls and ceilings (gloss > 25@60°) (water-base): 150 g/l (2007) / 100 g/l (2010)  
Cat. D: Interior/exterior trim and cladding paints for wood, metal or plastic (water-base): 150 g/l (2007) / 130 g/l (2010)  
UNIMARC SMALTO SETA Contains max: 100 g/l VOC

The product does not require labelling per the provisions of 67/548/CEE and 1999/45/CE and subsequent changes and amendments. Use the product according to current health and safety regulations; after use, do not discard the containers in the environment; allow the residue to dry thoroughly, then treat as special waste. Store out of the reach of children. Use in a well ventilated place. In case of contact with eyes, wash immediately with abundant running water. In caso of ingestion, see a physician immediately and show him or her the container or label. Do not dispose of residues in the sewers, waterways or ground. For more information consult the safety data sheet.

## КРАТКОЕ ОПИСАНИЕ

Applications, on previously prepared surfaces, of UNIMARC SMALTO SETA Water-based satin top coat series 300 - with a base of water-based acrylic resins and colouring pigments with a high degree of light stability - with at least 2 coats, for a minimum consumption of 140 ml/sq m.  
Supply and application of the material €. .... per sqm.