

SAN MARCO
is a brand of
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia

info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Vernice Acrilica

ВОЗДУХОПРОНИЦАЕМОЕ ЗАЩИТНОЕ ПОКРЫТИЕ ДЛЯ КАМНЯ



822

VERNICE ACRILICA - V.2024-09-24

ОПИСАНИЕ

VERNICE ACRILICA - воздухопроницаемое защитное средство на основе акриловых растворимых смол, обладает высокой эластичностью, способностью укреплять поверхность, водоотталкивающей способностью и прекрасной устойчивостью к химическим и атмосферным воздействиям. VERNICE ACRILICA - укрепляющий материал, специально предназначенный для защиты материалов из камня от загрязнений окружающей среды.

ОСНОВА НАНЕСЕНИЯ

The product can be applied on:
- calcareous stones, marble and stone featuring low porosity;
- exposed brickwork;
- concrete.

ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

- Type of Binder: reversible methacrylic resins
- Solvent: aromatic hydrocarbons
- Specific gravity per UNI EN ISO 2811-1: 0.90 ± 0.05 kg/l
- Viscosity per UNI 8902: 72 ± 16 cps at 25°C
- Gloss per UNI EN ISO 2813:
8220230 gloss finish: >80 , at 60°
8220238 satin finish: 50 ± 5 , at 85°
- Drying times (at 25°C and 65% R.H.):
. touch dry in 2 hours;
. coatability after 24 hours.

ПОДГОТОВКА ПОВЕРХНОСТИ

Stones or brickwork:
- Dust and clean the surfaces; in the event of a film of dirt, crust on the surface, flaking etc., clean using a water cleaning machine, water sandblasting, micro-

sandblasting or chemical cleaning. It is advisable to perform a preliminary test in order to determine the most effective method and type of cleaning.

- Where the surface is affected by mould, treat the surface with COMBAT 222 Detergent 4810222 and with COMBAT 333 Restorer 4810333 (see relevant technical sheets).

- Proceed with the application of 2 coats of VERNICE ACRILICA on a dry surface according to the instructions.

ИНСТРУКЦИИ ПО НАНЕСЕНИЮ

Air and surface conditions:

Air temperature: Min. +8 °C / Max. +35 °C.

Relative humidity of the air: <75%.

Temperature of the surface: Min. +5 °C / Max. +35 °C.

Humidity of the surface: <10% R.H.

- Avoid applying the product when there is condensation on the surface, or in direct sunlight.

- N. coats: at least 2 coats of the product should be applied.

- Tools: brush, spray gun.

- Thinning: at 0-20% with Synthetic thinner 5210011 or Thinner for quick-drying enamels 5070712 depending on the absorption of the surface

- When applying on stones or brickwork, apply 2 coats of product, allowing at least 12 hours between coats.

- Tools should be cleaned immediately after use using Synthetic thinner 5210011 or Thinner for quick-drying enamels 5070712.

- Indicative spreading rate: 4-6 sq m/l based on 2 coats

It is advisable to perform a preliminary test on the specific surface in order to determine the actual consumption.

КОЛЕРОВКА

The product is available in colourless gloss (cod. 8220230) and satin-finish (cod. 8220238) versions

ХРАНЕНИЕ

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 2 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

УКАЗАНИЯ ПО ТЕХНИКЕ БЕЗОПАСНОСТИ

Произведен в соответствии с директивами Евросоюза (2004/42/EC):

Категория A/h: фиксатор грунтовка (на базе растворителя): 750 г/л (2010)

содержит не более 750 г/л летучих органических соединений (ЛОС)

воспламеняется.

Транспортировка, применение и хранение материала выполняются согласно действующим гигиеническим нормам и технике безопасности; по окончании работы не разбрасывать тару бесконтрольно, а дать остаткам полностью высохнуть и сдать в специальные отходы. За дополнительной информацией обратиться к паспорту безопасности.

КРАТКОЕ ОПИСАНИЕ

Application, on preprepared surfaces, of VERNICE ACRILICA Clear preservative for stones cod. 8220230/238 with a base of methacrylic resins dispersed in a solution, specifically formulated for protecting stone materials.
Supply and application of the material €. per sq m.