

SAN MARCO
is a brand of
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia

info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Zincatura A Freddo

АНТИКОРРОЗИЙНЫЙ ГРУНТ ДЛЯ ЖЕЛЕЗА



CODE 1010110

ZINCATURA A FREDDO - V.2024-09-23

ОПИСАНИЕ

ZINCATURA A FREDDO - антикоррозийная краска основы для металлических основ для внутренних или внешних работ, на основе синтетических смол и металлического цинка. Материал обладает высокой антикоррозийной способностью гальванического вида, полученной антиоксидантным действием, выполняемым пигментами, входящих в состав. Материал рекомендуется для морской среды, тяжелой промышленности или, в целом, для суровых климатических условий.

ОСНОВА НАНЕСЕНИЯ

The product can be applied on exterior/interior metalwork in general. ZINCATURA A FREDDO must be recoat after no more than 7 days from the application.

ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

- Type of Binder: synthetic resins
 - Solvent: aliphatic hydrocarbons
 - Specific gravity per UNI EN ISO 2811-1: 2.14 ± 0.05 kg/l
 - Viscosity per UNI 8902: 9000-12000 cps at 25 °C
 - Appearance: mat
 - Drying (at 25 °C and 65% R.H.): to touch in 1 hour; to recoat after 16 hours.
- COATABILITY: with all SAN MARCO synthetic and quick-drying enamels

ПОДГОТОВКА ПОВЕРХНОСТИ

- Ferrous metalwork never previously painted:
- Remove any compact and adherent calamine and all traces of rust by means of commercial-type sandblasting (Grade SA2), or clean mechanically or manually.
 - In the case of new surfaces which do not feature calamine or rust, simply remove any grease from the surface using cleaning thinner.
 - Dust the surface, make sure the surface is perfectly dry, and apply 2 coats of

ZINCATURA A FREDDO.

- Proceed with the application of the desired finishing product.

Painted ferrous metalwork:

- Remove any layers of old flaking paint and any rust by means of mechanical or manual cleaning, rub down in order to coarsen any old paint which is still perfectly adherent.
- Remove dust from the surface.
- In the case of considerably deteriorated surfaces, it is advisable to remove any old paint and rust completely by means of grade SA2 1/2 sandblasting, or using the SVERNICIATORE SM10 paint remover cod. 5610014 followed by careful mechanical or manual cleaning.
- Any surfaces sandblasted down to reveal the original shine of the metal must receive their base coat of ZINCATURA A FREDDO after no more than 8 hours.
- Proceed with the application of the desired finishing product.

ИНСТРУКЦИИ ПО НАНЕСЕНИЮ

Air and surface conditions:

Air temperature: Min. +5 C / Max.+35 C.

Relative humidity of the air: <80%.

Temperature of the surface: Min. +5 C / Max. +35 C.

Dry surface

- Avoid applying the product when there is condensation on the surface, or in direct sunlight.
- Tools: brush.
- Stir the product carefully before use.
- Thinning: at 3% with White spirit 5200010 or Synthetic thinner 5210011.
- Application by spraying gun may be applied only in authorized factory (Dir. 2001/42/EC), thinning at 8% with White spirit 5200010 or Synthetic thinner 5210011.
- N coats: 2 coats must be applied
- Tools should be cleaned immediately after use using White spirit or Synthetic Thinner 5210011.
- Indicative spreading rate: 5 sq m/l based on 2 coats, corresponding to a dry film approx. 50 microns thick.

КОЛЕРОВКА

The product is available in the colour grey.

ХРАНЕНИЕ

Максимальная температура хранения материала: +30°C

Минимальная температура хранения: +5°C

Срок хранения материала составляет 3 года при условии хранения в закрытых оригинальных упаковках при соблюдении надлежащих правил хранения и температурного режима.

УКАЗАНИЯ ПО ТЕХНИКЕ БЕЗОПАСНОСТИ

Предельное значение EU (Дир. 2004/42/EC)

Кат. A/i : однокомпонентные краски высокого качества (на базе растворителя): 500 г/л (2010)
содержание: 500 г/л ЛОВ

воспламеняется.

Транспортировка, применение и хранение материала выполняются согласно действующим гигиеническим нормам и технике безопасности; по окончании работы не разбрасывать

тару бесконтрольно, а дать остаткам полностью высохнуть и сдать в специальные отходы.
За дополнительной информацией обратиться к паспорту безопасности.

КРАТКОЕ ОПИСАНИЕ

Applications, on previously prepared surfaces, of ZINCATURA A FREDDO Anticorrosive primer. cod. 1010110 - with a base of synthetic resins and metallic zinc - with at least 2 coats for a minimum consumption of 200 ml/sq m.
Supply and application of the material €. per sq m.