

**SAN MARCO**  
is a brand of  
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP  
Via Alta 10/A - 30020  
Marcon (Venezia), Italia

info@sanmarcogroup.com  
+39 041 4569322  
www.sanmarcogroup.com

# Acrisyl Pittura Riempitiva

ACRYLIC-SILOXANIC WATER-BASED HIGHLY WASHABLE OUTDOOR FILLER PAINT  
ANTI-MOLD ANTI-ALGAE

EN 1062-1 classification:  
G<sub>3</sub> E<sub>3</sub> S<sub>2</sub> V<sub>1</sub> W<sub>3</sub> A<sub>0</sub> C<sub>0</sub>



SERIES 634

ACRISYL PITTURA RIEMPITIVA - V.2024-11-06

## DESCRIPTION

ACRISYL PITTURA RIEMPITIVA anti-algae is a water-based outdoor paint with a base of acrylic-siloxanic resins in aqueous dispersion and filler aggregates, to protect outdoor wall surfaces.

It is suitable to re-paint wall finishing coating on thermal insulating system.

With features like high water repellence, high washing resistance, resistance to atmospheric agents, pollution and the alkaline environment typical of concrete surfaces and plasters in general.

The best looking results are achieved by applying on very regular, firmly compact surfaces containing inert substances with a fine grain size.

## TECHNICAL SPECIFICATIONS

- Type of Binder: Acrylic copolymer modified with siloxane in aqueous dispersion

- Classification per UNI EN 1062-1: (paints for exterior)

.Gloss per EN ISO 2813: class G<sub>3</sub> (<10, matt)

.Dry film thickness per ISO 3233: class E<sub>3</sub> (100-200 µm)

.Grain size per EN ISO 787-18: class S<sub>2</sub> (<300 µm medium)

.Water vapour transmission rate per UNI EN ISO 7783-2: class V<sub>1</sub> (Sd<0,14 m high)

.Liquid water permeability per UNI EN 1062-3: class W<sub>3</sub> (W≤0,1 low)

.Crack-bridging per UNI EN 1062-7A: class A<sub>0</sub> (no requirement)

.CO<sub>2</sub> permeability per UNI EN 1062-6: class C<sub>0</sub> (no requirement)

Other characteristics

- Specific gravity per UNI EN ISO 2811-1: 1,45-1,6 kg/l

- Maximum filler grain size: 125 µm

- Wet-scrub resistance per UNI 10560: >10000 cycles, excellent

- Alkali resistance per UNI 10795: alkaliproof

- Mould and algae resistant per UNI EN 15457 and UNI EN 15458

- Masonry preservative in conformity with the Kuenzle theory per DIN 18550:

$W < 0,5 \text{ kg/m}^2\text{h}^{0,5}$  and  $S_d < 2$  meters

- Classification of reaction to fire EN13501-1: Class A2 s1 d0

Referred to a consumption not exceeding that indicated, and to an application on a non-combustible surface.

- Drying time (at 25 °C and 65% R.H.): to touch in 30 min; to recoat after 4 hours.

## INSTRUCTIONS FOR USE

May be applied on:

- New and old plasters based on hydraulic binders.
- Concrete surfaces.
- Old paints and wall coatings that are organic or mineral in nature, dry, compact, absorbent and cohesive.
- Mineral conglomerates of various kinds, as long as they are absorbent.

Surfaces should be adequately prepared by following the instructions given in the paragraph 'PREPARING THE SURFACE'.

Do not apply on freshly painted surfaces.

## PREPARING THE SURFACE

- Make sure that the surface is thoroughly dried and aged. Resurface or consolidate using specific products if necessary.

- If mold is present, treat the surface with COMBAT 222 cleanser code 4810222, and with COMBAT 333 reconstruction code 4810333.

- Brush or wash to remove any efflorescence and any old peeling paint. Completely eliminate any raised layers of lime-based or tempera paints.

- Remove any dust, smog or other deposits by brushing.

Plaster surfaces:

- Cracks must be adequately widened and filled with stucco or similar products.

- Level any irregularities in the surface. Treat any holes, cracks, crevices and gaps with BETOMARC FIT 9740150, RASAMIX FIT 9670160, MARCOPRO 975 according to the type of support.

- Make sure that the support is completely dry and apply a coat of IDROFIS 4700006 acrylic water-based wall fixative, or ISOMARC 4410111 solvent-based wall fixative, or micronized solvent-free fixative ATOMO 8840001. On very absorbent plaster, can be applied one coat of NEPTUNUS PRIMER H code 0760230, to give an hydrophobic surface.

- On non uniforme surfaces, it's possible to apply one coat of ACRISYL GRIP code 9320019 levelling base.

- Apply ACRISYL PITTURA RIEMPITIVA.

Concrete surfaces:

- Remove any crumbling structural cement.

- The metal reinforcement disks visible on the surface must be carefully brushed and treated with BETOXAN PRIMER 9490125 passivating agent.

- Restore the missing parts with the smoothing coats BETOXAN 400 or BETOXAN 300 Non-shrinking thixotropic fiber-reinforced mortar 9490140/0130; perform the final smoothing with BETOXAN 100 or BETOXAN 200.

- On a clean, dry surface apply IDROFIS 4700006 acrylic water-based wall fixative or ATOMO 8840001 micronized solvent-free fixative.

- On non uniforme surfaces, it's possible to apply one coat of ACRISYL GRIP code 9320019 levelling base.

- Apply ACRISYL PITTURA RIEMPITIVA.

(The dilution of the primer and amounts to be applied depend on the absorption of the support surface, and must be determined through preliminary tests on the

specific support surface).

## APPLICATION INSTRUCTIONS

- Air and support surface conditions:  
Air temperature: Min. +8 °C / Max. +35 °C  
Relative environmental humidity: <75%  
Support surface temperature: Min. +5 °C / Max. +35 °C  
Moisture level of the support surface: <10%
- Avoid applying when surface condensation is present, or in direct sunlight.
- To avoid compromising the optimal appearance and performance of the product, we recommend that it be applied only in the aforementioned climate conditions, and that the surfaces be protected from rain and damp for approximately 48 hours. This will allow the product to dry completely and ensure even polymerization, which takes place in approximately 10 days.
- Surfaces bathed by rainwater during the approximately 10 days, could show translucent vertical lines. Such an occurrence does not compromise the product's performance, and may be removed by high-pressure water cleansing or after subsequent rainfalls.
- Application on surfaces with salt efflorescence or subject to rising damp may interfere with the product's adherence to the support. It is therefore necessary to first reconstruct the masonry using dehumidifying plasters, then paint with the SCUDOSIL siloxanic system.
- The protection of anti-mold and anti-algae finishes is of sacrificial nature: the efficacy and durability are strongly influenced by the severity of the environmental and climatic exposure, the building category, and the application system selected.
- Tools: brush or woolen roller
- Nr coats: at least 2 coats.
- We recommend applying the first layer by brush and the second by woolen roller.
- Dilution: first layer 35-40% with water; 20-25% for the second brushed layer; 10-15% for the second layer by woolen roller.
- Airless application is not recommended due to the abrasive action of the product filler.
- Clean tools with water immediately after use.
- Indicative covering capacity: 4-5 m<sup>2</sup>/l for smooth finishes and 3-4 m<sup>2</sup>/l for slightly bumpy finishes, referring to 2 layers on smooth surfaces with average absorbency. The actual yield is best determined by performing a preliminary test on the specific support surface.

## TINTING

Colors are obtainable via the color matching system and using COLORADO series 548 colorants.  
When using multiple batches it is recommended to remix the various products together to avoid slight differences in shading.  
For outdoor tasks it is a good rule of thumb to always use material from the same batch, from corner to corner. For tasks where it is unavoidable to continue on a wall with a different batch, do not place the batches contiguously. For the transition point, use any interruptions in the continuity of the surface: moldings, corners, cables, etc.

## STORAGE

Maximum temperature for storage stability: +30 °C  
Minimum temperature for storage stability: +5 °C  
The product should be preferably used within 2 years from date of manufacture when stored in original unopened containers and in appropriate temperature

conditions.

## SAFETY RULES

Limit value EU (Dir. 2004/42/EC)

Cat. A/c: Coatings for exterior walls of mineral substrate (water-base): 40 g/l (2010)

The product contains max: 40 g/l VOC

Harmful to aquatic life with long lasting effects.

The product must be transported, used and stored in accordance with the standards in force regarding hygiene and safety; let the residues dry out completely and treat them as special waste. Consult the safety sheet for additional information.

## SPECIFICATION ITEM

Highly washable anti-algae anti-mould filler paint for outdoor use.

Application, on prepared surfaces, of at least two coats of ACRISYL PITTURA RIEMPITIVA series 634 water-based paint based on acrylic-siloxanic resins in aqueous dispersion with excellent wet scrub resistant per UNI EN ISO 2811-1, high water vapour transmission rate per UNI EN ISO 7783-2 and low liquid water permeability per UNI EN 1062-3, in amount determined by the absorption of the support surface.

Supply and application of the material €.....m<sup>2</sup>.