

SAN MARCO
is a brand of
San Marco Group Spa

www.san-marco.com

SAN MARCO GROUP
Via Alta 10/A - 30020
Marcon (Venezia), Italia

info@sanmarcogroup.com
+39 041 4569322
www.sanmarcogroup.com

Tamstucco Pasta

ПАСТООБРАЗНАЯ ДЕКОРАТИВНАЯ ШТУКАТУРКА ДЛЯ ДЕРЕВЯННЫХ И
НАРУЖНЫХ ПОВЕРХНОСТЕЙ



CODE 9400006

TAMSTUCCO PASTA - V.2024-09-24

ОПИСАНИЕ

TAMSTUCCO - мелкорельефная штукатурка на водной основе, пастообразная для внутренних работ, используется для выравнивания различных основ стен или дерева. Материал может быть использован по деревянной поверхности, для заполнения впадин значительной толщины и выравнивания поверхности. TAMSTUCCO легко шлифовать, она обеспечивает хорошее сцепление последующих слоев красок и обладает хорошим прилеганием к основам.

ОСНОВА НАНЕСЕНИЯ

The product can be applied on:

- Lime mortar and cement lime mortar plaster; plaster with air-hardening lime and fine sand aggregate base, whether new or painted.
- Surfaces made of gesso, such as panels, partitions, division walls.
- Interior woodwork, before a covering painting system is employed.

TAMSTUCCO is a primer and must be paint over with a top coat finishing system.

ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

Binder: vinyl copolymer in water-based emulsion

Solvent: water

-Specific gravity per UNI EN ISO 2811-1: 1.90 ± 0.10 kg/l

-Appearance: white paste featuring high viscosity

-Drying (at 25 C and 65% R.H.): sandable after 1 hour; coatability after 6 hours.

COATABILITY: with all SAN MARCO emulsion paints and alkyd enamels, subject to the application of fixative.

If painting over with UNIMARC water-based products, the use of TAMSTUCCO 9400009 is recommended.

ПОДГОТОВКА ПОВЕРХНОСТИ

Plaster:

- Make sure that the surface has a maturing time of at least 28 days.

- Check the state of repair. The surface must be consistent. If this is not the case, take measures to reconstruct and strengthen the surface using specific products.
- Remove any efflorescence by buffing or washing.
- Where the surface features traces of old paint, remove any parts which are flaking and which are not perfectly adherent, whilst thick coats of lime-based paint or distemper must be removed completely by wetting the surface thoroughly and scraping, or using a water cleaning machine.
- Apply TAMSTUCCO by means of successive passes with a plastering trowel to level and fill in order to achieve surface smoothing, or using a putty knife in order to fill the cracks and depressions.
- Proceed with the application of the fixative, chosen on the basis of the type of paint used for the finishing system.

Woodwork:

- Sand lightly in order to remove the raised wood fibres.
- Eliminate any coats of old flaking varnish and coarsen all the surfaces which have already been varnished.
- Remove any resin using the Nitro thinner 5170076.
- Fill any imperfections using TAMSTUCCO.
- Sand and, after approx. 6 hours, apply the fixative.
- Proceed with the painting system.

ИНСТРУКЦИИ ПО НАНЕСЕНИЮ

Air and surface conditions:

Air temperature: Min. +5 C / Max. +35 C.

Relative humidity of the air: <80%.

Temperature of the surface: Min. +5 C / Max. +35 C.

- The product can be applied using a plastering trowel or putty knife.
- The product is ready to be used.
- Tools should be cleaned immediately after use using water.
- Indicative spreading rate: highly variable depending on the type of surface. With an applied thickness of 500-600 microns, a spreading rate of 1 sq m/kg is obtained. It is advisable to perform a preliminary test on the specific surface in order to determine the actual consumption.

КОЛЕРОВКА

The product is compatible with the colouring pastes of the Marcromie tinting system provided only the lighter shades are used.

ХРАНЕНИЕ

Максимальная температура хранения материала: +30°C

Минимальная температура хранения: +5°C

Срок хранения материала составляет 2 года при условии хранения в закрытых оригинальных упаковках при соблюдении надлежащих правил хранения и температурного режима.

УКАЗАНИЯ ПО ТЕХНИКЕ БЕЗОПАСНОСТИ

Произведено в соответствии с директивами Евросоюза 2004/42/EC (d. lgs. 161/2006)

Применять материал согласно действующим нормам гигиены и безопасности; после использования запрещено выбрасывать упаковки в окружающую среду, остатки материала должны быть полностью высушены и утилизированы вместе со строительными отходами. Не выбрасывать отходы материала в канализацию, водоемы и на землю. Для дополнительной

информации необходимо ознакомиться с Листом Безопасности.

КРАТКОЕ ОПИСАНИЕ

Applications, on preprepared interior surfaces, of TAMSTUCCO Water-borne wood or wall filler in paste cod. 9400006 - with a base vinyl copolymer in water-based emulsion - for levelling imperfections on walls or woodwork.